



Hammond Road • Elms Estate • Bedford MK41 0ND • England  
Telephone: +44 (0) 1234 364411 • Fax: +44 (0) 1234 271486  
Email: [info@terinex.co.uk](mailto:info@terinex.co.uk)  
Website: [www.terinex.co.uk](http://www.terinex.co.uk)

## TECHNICAL SPECIFICATION SHEET FACIAL TISSUES

PROPERTIES	VALUES	UNITS
Colour	White	/
Pulp	Virgin Fibre	/
Plies	2	/
Basis Weight	14 +/- 0.5	g/m <sup>2</sup>
Moisture (min)	5.0-6.5	%
Thickness	60-80	Micron
Softness	10.5	Manual
Tensile M.D* (min)	110-120	gr/15mm/ply
Tensile T.D** (min)	55-60	gr/15mm/ply
Elongation M.D (min)	11-14	%
Elongation T.D (min)	2-4	%

\*MD – Machine direction

\*\*TD – Transverse direction

**The figures quoted are nominal values and are to be used as such**

Issue No : 3

Issue date – February 2014